



Features

- Wide temperature range -55°C to 110°C^*
- Thermoset Insulation
- Superior mechanical properties
- Flexible construction
- Flame retardant
- Excellent fluid/oil resistance
- Moisture and sunlight resistant

Performance Standards

- Meets AAR RP-585/S-501
- Insulation IAW ICEA S-66-524 (S-95-658)
- Passes NFPA 130-2014
- Meet the requirements of UL 1685 (FT4/IEEE 1202 with smoke measurement)
- Meet the requirements of 49 CFR Part 238 for flame and smoke requirements (ICEA S-19-81)
- Meet the requirements of ASTM E662 in flaming and non-flaming modes
- Meet the transit toxicity requirements when tested in accordance with BSS 7239
- Passes UL VW-1 flame test,
- Passes IEEE-383 1974 vertical tray flame test

Construction

Conductor: Annealed, Tinned copper per ASTM B33, B172, AAR S-501, and AAR RP-585

Insulation: Crosslinked polyolefin, Exane® (colors – as required)

Scope

Exane®-1068A transit wire is a tough, flame retardant construction ideally suited for rugged transportation industry applications. It has a high temperature rating yet will not crack at temperatures down to -55°C . Exane® transit wire has much better resistance to cut-through, crush, and scrape abrasion than rubber, EPR, Neoprene and Hypalon. It is also more flexible and has better overload characteristics than fluoropolymers. Exane® transit wire has good moisture and oil resistance, excellent fire resistance, and low smoke and acid gas generation characteristics.

CHICAGO

933 E. Remington Rd
Schaumburg, IL 60173
847.944.1500

BOSTON

100 Jytek Drive
Leominster, MA 01453
978.534.5300

ATLANTA

5940 Cabot Parkway
Alpharetta, GA 30005
678.297.1080

PHOENIX

1524 W 14th St
Tempe, AZ 85281
623.478.8700

Exane®-1068A Transit Wire



110°C* Transit Wire
2000 Volt
AAR S-501/RP-585
(XLPO)
Spec. DAA1068A

Product Number	Conductor Size (AWG)	Stranding	Insulation Wall (Inch) (mm)		Nom. Diameter (Inch) (mm)		Ampacity* @110°C	Aprox. Weight (lbs/1000 ft) (kg/km)	
TXE-18-2KV	18	19/30	0.045	1.14	0.139	3.53	18	15	22.4
TXE-16-2KV	16	19/29	0.045	1.14	0.146	3.71	24	17	25.3
TXE-14-2KV	14	19/27	0.045	1.14	0.159	4.04	39	22	32.8
TXE-12-2KV	12	19/25	0.045	1.14	0.177	4.50	51	31	46.2
TXE-10-2KV	10	27/24	0.045	1.14	0.208	5.28	67	50	74.5
TXE-8-2KV	8	37/24	0.055	1.40	0.252	6.40	85	69	102.9
TXE-6-2KV	6	61/24	0.055	1.40	0.304	7.72	120	108	161.0
TXE-5-2KV	5	91/24	0.055	1.40	0.354	8.99	145	155	231.1
TXE-4-2KV	4	105/24	0.055	1.40	0.376	9.55	160	177	263.9
TXE-3-2KV	3	125/24	0.055	1.40	0.401	10.19	180	202	301.2
TXE-2-2KV	2	150/24	0.055	1.40	0.431	10.95	214	240	357.8
TXE-1-2KV	1	225/24	0.065	1.65	0.523	13.28	247	359	535.2
TXE-1/0-2KV	1/0	275/24	0.065	1.65	0.563	14.30	286	431	642.6
TXE-2/0-2KV	2/0	325/24	0.065	1.65	0.585	14.86	329	478	712.7
TXE-3/0-2KV	3/0	450/24	0.065	1.65	0.683	17.35	380	673	1003.4
TXE-4/0-2KV	4/0	550/24	0.065	1.65	0.708	17.98	446	786	1171.9
TXE-262-2KV	262	650/24	0.075	1.90	0.785	19.94	524	920	1371.6
TXE-313-2KV	313	775/24	0.075	1.90	0.853	21.67	590	1090	1625.1
TXE-373-2KV	373	925/24	0.075	1.90	0.908	23.06	657	1285	1915.8
TXE-444-2KV	444	1100/24	0.075	1.90	0.978	24.84	734	1520	2266.2
TXE-535-2KV	535	1325/24	0.090	2.29	1.085	27.56	828	1850	2758.2
TXE-646-2KV	646	1600/24	0.090	2.29	1.23	31.24	931	2250	3354.5
TXE-777-2KV	777	1925/24	0.090	2.29	1.3	33.02	1047	2655	3958.4
TXE-1111-2KV	1111	2750/24	0.120	3.05	1.58	40.13	1254	3810	5680.4

1. The Exane® insulation family has outstanding mechanical and electrical test characteristics. It also has excellent long-term moisture resistance and heat aging characteristics. See the above specification for details.
2. Normal stock color is dark grey. Striping is also available.

* These ampacities are based on single conductors in air with an ambient of 40°C and conductor temperature of 110°C.



CHICAGO
933 E. Remington Rd
Schaumburg, IL 60173
847.944.1500

BOSTON
100 Jytek Drive
Leominster, MA 01453
978.534.5300

ATLANTA
5940 Cabot Parkway
Alpharetta, GA 30005
678.297.1080

PHOENIX
1524 W 14th St
Tempe, AZ 85281
623.478.8700

For sales inquiries: sales@electrowire.com